

PATENT ABSTRACTS OF JAPAN

(11)Publication number : 10-168297

(43)Date of publication of application : 23.06.1998

(51)Int.Cl.

C08L 69/00
 C08K 3/32
 C08K 3/34
 C08K 5/521
 C08K 7/14
 C08L 67/00
 //(C08L 69/00
 C08L 67:00
 C08L 21:00
 C08L 27:12
 C08L 83:04)

(21)Application number : 08-353557

(22)Date of filing : 16.12.1996

(71)Applicant : KANEGAFUCHI CHEM IND CO LTD

(72)Inventor : OONO YOSHITAKA
 OHARA YOICHI
 FUJITA KATSUTOYO
 MATSUMOTO KAZUAKI
 KOYAMA HIROSHI
 HIROBE KAZUFUMI

(54) FLAME-RETARDANT THERMOPLASTIC RESIN COMPOSITION

(57)Abstract:

PROBLEM TO BE SOLVED: To obtain a flame-retardant resin composition which has an excellent molding flow and can give a molding having an excellent flame retardancy and heat resistance and persistent stabilized flame retardancy and deforming little even under high-temperature high-humidity conditions by mixing a mixture comprising a polycarbonate resin and a polyester resin with a limited organophosphorus flame retardant and a stabilized red phosphorus flame retardant in a specified ratio.

SOLUTION: This composition comprises 100 pts.wt. mixture comprising a polycarbonate resin (A) and a thermoplastic polyester resin (B) in a ratio of 85/15 to 50/50 by weight, 1-11 pts.wt. organophosphorus flame retardant (C) represented by the formula (wherein m1, m2, m3 and m4 are each 0-2; and n is 1-15) and 0.05-5 pts.wt. stabilized red phosphorus flame retardant (D). Component A is desirably made from bisphenol A and has desirably a viscosity-average molecular weight of 18,000-35,000. Component B used is exemplified by polyethylene terephthalate. An example of component C is bisphenol A poly(diglycidyl)phosphate. Component D is exemplified by red phosphorus coated with e.g. a thermosetting resin.

